

In The Claims:

This listing of claims will replace all prior versions, and listings of claims in the application.

1. (Previously Presented) A photosensitive resin laminate comprising a support, an adhesive layer and a photosensitive resin layer, wherein the photosensitive resin laminate shows a total light transmission of not less than 60% and wherein the photosensitive resin layer has a thickness of not less than 500 μm .

2. (Previously Presented) The photosensitive resin laminate of claim 1, wherein the photosensitive resin layer has a Shore D hardness of not less than 50.

3. (Original) The photosensitive resin laminate of claim 1, wherein the photosensitive resin layer has an absorbance at 400 nm - 600 nm of not more than 0.3.

4. (Original) The photosensitive resin laminate of claim 1, wherein the photosensitive resin layer has a scattering rate of not more than 25%.

5. (Original) The photosensitive resin laminate of claim 1, wherein the photosensitive resin layer has a turbidity of not more than 3.5.

6. (Original) The photosensitive resin laminates of claim 1, wherein the photosensitive resin layer contains a hydroxylamine derivative.

7. (Original) A plate for a signboard comprising the photosensitive resin laminate of claim 1.

8. (Previously Presented) A signboard having a relief, which comprises the photosensitive resin laminate of claim 1, wherein the photosensitive resin layer has a thickness of not less than 500 μm and is formed at least on the support via the adhesive layer, and a coating layer having a transmission at 400 nm of not more than 50% on its surface.

9. (Original) A signboard having a relief, which comprises the photosensitive resin laminate of claim 1, and a layer having an image laminated on a side of the support.

10. (Currently Amended) The signboard of claim 9, wherein the layer having the image is directly printed on ~~the back of~~ the support.

11. (Previously Presented) A photosensitive resin laminate comprising a support, an adhesive layer and a photosensitive resin layer, which laminate satisfying the following formula (1):

$$\{(A-B)/A\} \times 100 \leq 15 \quad (1)$$

wherein A is a total light transmission (%) of the support and B is a total light transmission (%) of the photosensitive resin laminate and wherein the photosensitive resin layer has a thickness of not less than 500 μm .

12. (Previously Presented) The photosensitive resin laminate of claim 11, wherein the photosensitive resin layer has a Shore D hardness of not less than 50.

13. (Original) The photosensitive resin laminate of claim 11, wherein the photosensitive resin layer has an absorbance at 400nm - 600 nm of not more than 0.3.

14. (Original) The photosensitive resin laminate of claim 11, wherein the photosensitive resin layer has a scattering rate of not more than 25%.

15. (Original) The photosensitive resin laminate of claim 11, wherein the photosensitive resin layer has a turbidity of not more than 3.5.

16. (Original) The photosensitive resin laminates of claim 11, wherein the photosensitive resin layer contains a hydroxylamine derivative.

17. (Original) A plate for a signboard comprising the photosensitive resin laminate of claim 11.

18. (Previously Presented) A signboard having a relief, which comprises the photosensitive resin laminate of claim 11, wherein the photosensitive resin layer has a thickness of not less than 500 μm and is formed at least on the support via the adhesive layer, and a coating layer having a transmission at 400 nm of not more than 50% on its surface.

19. (Original) A signboard having a relief, which comprises the photosensitive resin laminate of claim 11, and a layer having an image laminated on a side of the support.

20. (Currently Amended) The signboard of claim 19, wherein the layer having the image is directly printed on ~~the back of~~ the support.